

# TECHNICAL DATA

## PEN (Polyethylene Naphthalate) TAPE

**Product Code: 1PN2R  
(Flame Retardant)**



*P. Leo & Co Ltd*

Email : sales@bcwire.net



 UL File No. E126174

**Description :** P.LEO # 1PN2R PEN Electrical Insulating Tape is made by Teonex® Q51 Polyethylene naphthalate (PEN) film can perform an excellent thermal property at 180°C. It is superior in almost all fields of applications. It exhibits higher temperature rating, better dimensional stability after heating, better hydrolytic resistance and excellent oxygen permeability. This product complies with the flame Retardant requirements of UL 510.

**Application :** For use in high performance electrical applications, used on high-temperature coils, such as in traction machine manufacturing, in the production of generators, capacitors, transformers etc. PEN Tape can be applied as major in Class F 155°C, Class H 180°C and Class N 200°C Electrical Insulation System.

Technical Details :	<u>PROPERTIES</u>	<u>UNITS</u>	<u>SPECIFICATION</u>
	TOTAL THICKNESS	mm	0.055 ± 0.005
	TENSILE STRENGTH	kg/25mm	10
	ELONGATION	%	80 ± 30
	ADHESION TO STEEL	kg/25mm	0.6
	DIELECTRIC BREAKDOWN	Kv	6
	TEMPERATURE RATING	°C	155

**Color :** WH = white

**Test Method :** In accordance with ASTM method

**Shelf Life :** 6 months when storage at 73°F and 65% relative humidity

**Availability :** Standard 50 Meter roll, 3" core, width 960mm

### **Important Notice to Purchase**

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection therewith.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.

